

SUPER SAAK ADHESIVE

Polymer Modified Water Resistant Adhesive for Fixing Swimming Pools, Fountains & Watertanks Tiles



DESCRIPTION :

SUPER SAAK ADHESIVE is a cement-based dry-set mortar—just add water; ideal for fixing pool wall and floor ceramic tiles in 3–10 mm thickness.

ADVANTAGE :

- Factory controlled pre-blend ensures consistent high quality
- Superior bond in wet & immersed water conditions
- Easy tile installation that enables high productivity
- Excellent slip resistance
- Suitable for horizontal & vertical surfaces

USES:

SUPER SAAK ADHESIVE for use in all types of tiles for swimming pools , fountains, watertanks, and submerged conditions.

TECHNICAL DATA :

Appearance	Gray and White
Application Temperatu	+5 to 35 C
Mixture Rate	4 to 5 L Water/20kg
Coverage	4kg/1sqm (5mm thickness)
Storage	12 months below 20-30C closed sack
Solidification	25-30 minutes
Slither	less than 0.7N/sqmm
Adhesion	more than 1.6N/sqmm

STANDARDS COMPLIANCE :

SUPER SAAK ADHESIVE conforms to: • BS:EN 12004 as C2TE S1 • ISO 13007
• ASTM C348 & C349

INSTRUCTIONS FOR USE

The surface should be sound, clean, free from loose material, grease, laitance, dirt, curing compound, etc. Wet the all surfaces with clean water prior to the application of SUPER SAAK ADHESIVE. Surface should appear damp with no water pooling.

SURFACES :

SUPER SAAK can be applied directly on concrete, cement screeds, and cement or lime mortar. Special attention must be given to new construction prior to commencing tiling. Tiles should not be placed on concrete or blockwork until all shrinkage movemen-thastaken place.

MIXING :

For the preparation of mortar adhesive, pour into a container 4 - 5 liters of water for 20 Kg bag of SUPER SAAK ADHESIVE. Add the powder to the water and mix with a low speed electric drill fitted with a suitable paddle for 3-4 minutes, until auniform, lump-free consistency is achieved. Allow the mixed material to stand for about 10 minutes and remix briefly with no further water to be added. It can also be blended manually for small quantity but ensure correct amount of powder to water is maintained. If required, add 0.5Ltr of SAAK Bond SBR to the mixing water followed by addition of powder. Mixed material can be used within 2 hours. Do not add water to the mix, once the mortar adhesive starts to harden.

APPLICATION :

Spread the adhesive with a notched trowel, tile within 10–15 min, and adjust position if needed. Leave tiles undisturbed for 48 hrs. Fill joints after 2 days using SAAK Tile Grout.



SUPER SAAK ADHESIVE

Polymer Modified Water Resistant Adhesive for Fixing Swimming Pools, Fountains & Watertanks Tiles

COVERAGE :

When applied at a thickness of 2 - 3 mm, one bag will cover an area of 5 - 8 m². This however will be dependent on the conditions of the substrate and the type of tile used.

JOINTS :

It is recommended that when fixing ceramic tiles, a minimum spacing of 2mm be left around each tile.

YIELD :

20 kg bag of SUPER SAAK when mixed with 4.8 litres water will yield approximately 16 litres.

FINISHING :

Remove excess adhesive with a damp cloth before material has set.

PACKAGING :

SUPER SAAK is supplied in 20 kg sacks.

STORAGE :

Original sealed container of SUPER SAAK ADHESIVE has a shelf life of 12 months provided it is stored clear of ground in a dry shaded place between 20-30°C.

HEALTH AND SAFETY :

SUPER SAAK is cement based product. TECHNICAL DATA SHEET - SAAK Ceramic Premium FixCare should be taken to avoid inhalation of dust and contact with eyes

SAAK also provides various technical information such as CAD details, detailed method statements, specification clauses, application manuals, product selectors and technical support both in contractors and consultants offices as well as construction sites. For further information on these products and systems kindly check our website or contact your local SAAK representative.

